

玻纤增强PP PG20
GlassFiber Reinforced PP PG20
产品信息
General Information

| | |
|--------------------------|---|
| 特点 | ·20%玻纤增强 ·尺寸稳定 ·高强度 ·高耐热 |
| Features | ·20% GlassFiber Reinforced ·Excellent Dimensional Stability ·High Rigidity ·High HDT |
| 应用 | ·电器 ·汽车零部件 |
| Uses | ·Electronics ·Automobile parts |
| RoHS信息 | ·通过RoHS要求 |
| RoHS Compliance | ·RoHS Compliant |
| 形态 | ·粒子 |
| Forms | ·Pellets |
| 加工方法 | ·注塑 |
| Processing Method | ·Injection Molding |

产品性能
Product Properties

| 物理性能 | 测试标准 | 测试条件 | 单位 | 典型值 |
|------------------------------|----------------------|-----------------------|-------------------|----------------------|
| Physical | Test standard | Test Condition | Unit | Nominal value |
| 密度 | ISO 1183 | 23°C,50%H | g/cm ³ | 1.08 |
| Specific Gravity | | | | |
| 熔体流动速率 | ISO 1133 | g/10min | 230°C/2.16kg | 10 |
| Melt flow rate | | | | |
| 成型收缩率 | ISO 294 | 23°C,50%H | % | 0.4-0.8 |
| Mold Shrinkage | | | | |
| 力学性能 | | | | |
| Mechanical | | | | |
| 拉伸强度 | ISO 527 | 50mm/min | MPa | 72 |
| Tensile Strength | | | | |
| 断裂伸长率 | ISO 527 | 50mm/min | % | 8 |
| Tensile Elongation | | | | |
| 弯曲强度 | ISO 178 | 2.0mm/min | MPa | 110 |
| Flexural Strength | | | | |
| 弯曲模量 | ISO 178 | 2.0mm/min | MPa | 4500 |
| Flexural Modulus | | | | |
| 悬臂梁缺口冲击强度 | ISO 180 | 23°C,50%H | KJ/m ² | 8 |
| Izod Notched Impact Strength | | | | |
| 热性能 | | | | |
| Thermal | | | | |
| 热变形温度 H.D.T未退火 | ISO 75 | 0.45MPa | °C | 120 |
| Heat Deflection Temperature | | | | |
| 阻燃性 | | | | |
| Flammability | | | | |
| 水平燃烧 | UL-94 | 23°C,50%H | Class | HB |
| Horizontal Flammability | | | | |

注塑信息
Injection

| | |
|--------------------|-----------|
| 干燥温度 | 60-80°C |
| Drying Temperature | |
| 干燥时间 | 2-4h |
| Drying Time | |
| 后段温度 | 190~210°C |
| Rear Temperature | |
| 中段温度 | 210~230°C |
| Middle Temperature | |
| 前段温度 | 220~250°C |
| Front Temperature | |
| 喷嘴温度 | 230~260°C |
| Nozzle Temperature | |
| 模温 | 60°C-80°C |
| Mold Temperature | |

备注:

Note:

1. 所有数据基于本色或特定颜色，仅供选型参考。
All the data are based on uncolored grades or selected colors, provided for reference in grade selection only.
2. 样条测试前经过23°C 24h的预处理。
Test Bars pretreated 24h under 23°C before testing.

创合新材料科技江苏有限公司
Chuanghe New Material Technology Jiangsu Co., LTD